

NITRIDE SEMICONDUCTOR WAFER AND METHOD OF PROCESSING NITRIDE SEMICONDUCTOR WAFER

BACKGROUND OF THE INVENTION

Field of the Invention

5 This invention relates to distortion and smoothness of nitride semiconductor wafers which can be utilized as a substrate wafer for making blue light emitting devices (laser diodes (LDs) or light emitting diodes (LEDs)).

 This application claims the priority of Japanese Patent Application No.
10 2003-128060 filed on May 6, 2003 and Japanese Patent Application No. 2003-281647 filed on July 29, 2003, which are incorporated herein by reference.

Description of Related Art

 Sapphire (α -Al₂O₃) single crystals have been exclusively utilized as
15 substrate wafers for making InGaN-type blue light emitting diodes and InGaN-type blue light laser diodes. GaN thin films, InGaN thin films or other nitride thin films are heteroepitaxially grown on a sapphire single crystal wafer. Light emitting devices are produced by piling n-type and p-type GaN and InGaN thin layers epitaxially on the GaN thin film grown on
20 the sapphire wafer. Sapphire wafers are sold on the market and are easily obtained. Sapphire wafers have given satisfactory achievements as an essential part of blue light sources. Sapphire wafers, however, have weak points. Sapphire, which is an insulator, cannot lead electric current. Sapphire prevents us from making n-type or p-type sapphire. A sapphire

substrate forbids us to make an n-electrode on a bottom of a device chip. An n-electrode should be formed upon a conductive n-type GaN layer grown upon a sapphire substrate. Both p- and n-electrodes are formed upon a top of an LED or LD device chip.

5 The top n-electrode requires a wide extra surface for the device chips. Existence of the top n-electrodes inhibits device makers from reducing chip sizes of LEDs or LDs. The top electrode is one drawback of sapphire wafers. Another weak point of sapphire is non-cleavage. Sapphire ($\alpha\text{-Al}_2\text{O}_3$) has low symmetry which deprives the crystal of natural cleavage. High
10 mechanical rigidity is a further drawback for sapphire wafers. Without relying upon natural cleavage, a device-produced sapphire wafer is cut into individual chips by mechanical dicing, which raises manufacturing costs and lowers yields. Lattice misfitting between the sapphire wafer and GaN layers makes a lot of dislocations and degenerates a light emitting property of chips.

15 No GaN single crystal wafer has been available till now. Thin films of GaN are grown on a foreign material substrate. Use of sapphire substrates, silicon carbide substrates (SiC), gallium arsenide substrates (GaAs) and spinel substrates has been reported. The most prevalent foreign material substrate is a sapphire substrate as described hitherto. Since the
20 materials of substrates and films are different, strong stress occur at an interface between films and foreign material substrates. The films grown on the foreign substrate exfoliate from the substrate due to the strong stress at an early stage. For avoiding the exfoliation, interposition of a low-temperature grown buffer layer and separation growth of individual GaN nuclei via small
25 windows of a mask (ELO method) have been proposed. The low-temperature

made GaN buffer layer has a function of alleviating inner stress at a film/substrate interface. The ELO (epitaxial lateral overgrowth) method can make thin GaN layers on a sapphire substrate by covering the sapphire substrate with a mask (e.g., SiO₂ or SiN), perforating the mask into small windows regularly aligning in a hexagonal pattern composed of repetitions of many equilateral-triangles for exposing the underlying substrate via the window, growing GaN nuclei on the separated exposed windows and reducing the inner stress.

① PCT-application, WO99/23693, ② Japanese Patent Laying Open No.2000-22212(Japanese Patent Application No.10-183446), ③ Japanese Patent Laying Open No.2000-12900 (Japanese Patent Application No.10-171276), ④ Akira Usui, "Thick Layer Growth of GaN by Hydride Vapor Phase Epitaxy", IEICE, C-II Vol.J81-C-II No.1, pp.58-64, January 1998, ⑤ Kensaku Motoki, Takuji Okahisa, Naoki Matsumoto, Masato Matsushima, Hiroya Kimura, Hitoshi Kasai, Kikurou Takemoto, Koji Uematsu, Tetsuya Hirano, Masahiro Nakayama, Seiji Nakahata, Masaki Ueno, Daijirou Hara, Yoshinao Kumagai, Akinori Koukitu and Hisashi Seki, "Preparation of Large Freestanding GaN Substrates by Hydride Vapor Phase Epitaxy Using GaAs as a Starting Substrate", Jpn. J. Appl. Phys. Vol. 40 (2001) pp. L140-L143, describe the ELO of GaN films on GaAs or sapphire substrates. The ELO method, which is inherently a method of making thin films, can produce no thick layer. If a thick GaN layer piles on a substrate by the ELO method, a number of dislocations are produced and big inner stress is yielded. The large inner stress would exfoliate the GaN layer from the substrate. Thus, the ELO fails to make a freestanding GaN substrate. The ELO is

insufficient to produce a thick single crystal GaN substrate wafer. Another improvement is required for making GaN freestanding single crystal bulks besides the ELO.

⑥ Japanese Patent Laying Open No.2001-102307 (Japanese Patent Application No.11-273882), which has the same applicant as the present invention, proposed a facet growing method of GaN. Instead of maintaining a mirror-flat c-plane on the top, the facet growth method intentionally makes facets and facet pits, maintains the facets and the facet pits on a growing surface, displaces dislocations by the facets, gathers the dislocations from neighboring regions into centers of the facet pits, reduces dislocation density in other regions, and obtains low dislocation GaN single crystals. The facet growth method of ⑥ enabled us to make a large freestanding GaN wafer of good single crystal for the first time. ⑥ cannot predetermine spots of the facet pits, because ⑥ lacks a contrivance of determining positions of the pits and the pits are born at random spots.

⑦ Japanese Patent Laying Open No.2003-165799 (Japanese Patent Application No.2002-230925) gave the GaN facet growing method an improvement of predetermining the positions of facet pits by depositing seeds on an undersubstrate, making facet pits following to the seeds. The seeds initiate closed defect assembling regions (H). Positions of the closed defect assembling regions coincide with the positions of the seeds on the undersubstrate. Other parts except the closed defect assembling regions (H) are good single crystal GaN.

Polishing is another important matter for the present invention. Polishing technology has not matured for nitride semiconductors, since

independent, freestanding nitride crystal bulk wafers have not been produced on a practical scale yet. Thus, current polishing technology for other materials should be considered.

In the case of silicon semiconductors, silicon wafers are mechanically polished with alumina powder. Besides the mechanical polishing, processed silicon wafers having devices are polished for flattening rugged surfaces by chemical mechanical polishing (CMP) which makes use of colloidal silica and corrosive liquid. GaAs wafers are also treated with the chemical mechanical polishing (CMP), since some corrosive liquid for GaAs is known. People have believed that the CMP is impossible for sapphire and GaN. Sapphire is a refractory oxide. GaN is a sturdy nitride. Sapphire and GaN are chemically stable materials. A corrosive liquid for sapphire and GaN has not been reported.

⑧ Japanese Patent Laying Open No.10-166259 (166259/1998) (Japanese Patent Application No.8-332120) declared that it proposed a chemical mechanical polishing (CMP) of sapphire for the first time by an alkali liquid. However, ⑧ makes a secret of details of the polishing liquid. ⑧ disclosed no concrete components of the alkali liquid. Nobody can obtain knowledge of the detail of the alkali. What is the alkali liquid as a polishing liquid for sapphire is still outstanding in spite of ⑧.

⑨ J. L. Weyher, S. Muller, I. Grzegory and S. Porowski, "Chemical polishing of bulk and epitaxial GaN", Journal of Crystal Growth 182 (1997), p17-22, reported that they CM-polished GaN (0001) crystal bulks with an NaOH or KOH solution. But, ⑨ insisted that CMP (chemical-mechanical polishing) was still impossible for high quality GaN crystals.

⑩ J. A. Bardwell, J. B. Webb, H. Tang, J. Fraser and S. Moisa, "Ultraviolet photoenhanced wet etching of GaN in $K_2S_2O_8$ solution", J. Appl. Phys., vol. 89, No.7, p4142-4149, (2001), disclosed that GaN was wetly etched with a $K_2S_2O_8$ solution.

5 ⑪ Japanese Patent Laying Open No.2002-356398 (Japanese Patent Application No.2001-166904) was contrived by the same inventor as the present invention and related to chamfering of a periphery of a GaN wafer. Freestanding circular GaN wafers had not existed, but it was possible to make them for the first time. Therefore, the inventor contrived to chamfer the
10 periphery of the GaN wafer and to make OF for indicating a specified direction.

The technology of making a bulk GaN single crystal wafer is not fully matured yet. Technology of producing AlN and InN is far behind GaN. 50mm ϕ (2-inch ϕ) freestanding GaN single crystal wafers are not produced on
15 a commercial scale and do not come onto the market yet. The applicant of the present invention has a potential of making a circular 50mm ϕ GaN freestanding single crystal wafer. 45mm ϕ GaN wafers are also available for the applicant. Circular GaN freestanding wafers larger than 45mm ϕ are suitable for substrate wafers for making light source devices (LEDs and LDs)
20 owing to circularity and size-sufficiency. However, such large GaN wafers made by the state-of-the-art technology are annoyed by poor flatness, large distortion and bad roughness. GaN bulks made in vapor phase are annoyed by large distortion height H which randomly ranges between 200 μ m and 30 μ m. Thickness fluctuation exceeds 50 μ m. Due to lack of a pertinent polishing
25 method, surface roughness is over 10 μ m. No circular GaN wafers prepared

by the current technology satisfy the requirements of flatness, thickness uniformity and smoothness at present yet. GaN is chemically stable and physically rigid. GaN, however, is not tough and fragile. It is not easy to polish chemically-tenacious, physically-rigid but fragile GaN crystals.

5 Slight physical shocks easily break GaN crystals. GaN, which has a hexagonal system, has asymmetric plane properties for a (0001)-plane and (000-1)-plane. The (0001)-plane is a surface consisting of Ga atoms. Thus, the (0001)-plane is sometimes called "(0001)Ga-plane". The (000-1) plane is a surface consisting of N-atoms. The (000-1) surface is called

10 "(0001)N-plane". Two surfaces of the Ga-plane and N-plane are different in chemical and physical properties. Namely, the chemical and physical properties of GaN wafers have orientation dependence. The chemical obstinacy, physical rigidity, fragility and orientation dependence enhance difficulties of lapping (grinding) and polishing (whetting) of GaN bulk

15 crystals.

GaN is transparent for visible light. A GaN wafer looks like a glass plate. Silicon (Si) wafers or gallium arsenide (GaAs) wafers are opaque. Unlike Si or GaAs, GaN wafers have difficulty of discriminating a top or bottom surface by difference of finishing for the top/bottom.

20 GaN has other many problems. Here, attention should be paid to distortion and roughness of GaN bulk crystals. GaN has a hexagonal system having three-fold symmetry around a c-axis. A large GaN crystal is unobtainable. A foreign material plate is employed as a starting substrate, which is called an "undersubstrate" for distinguishing the object GaN

25 substrate wafer. For example, a GaAs (111) single crystal plate is adopted

for an undersubstrate.

Collaboration of the ELO method and the facet-growth method grows a thick GaN single crystal layer on the (111) GaAs substrate in vapor phase. Then, the GaAs undersubstrate is eliminated and a GaN freestanding thick layer is obtained. GaAs and GaN have large lattice misfitting and big thermal expansion rate difference. The lattice misfit and thermal expansion difference cause large inner stress in the GaN film. The large stress is released by eliminating the GaAs undersubstrate. The released inner stress deforms the GaN film. Distortion is a serious problem for the GaN wafers.

A top convex distortion in which a top surface lifts at the center upward is defined as a positive distortion. A top concave distortion in which a top surface sinks at the center is defined as a negative distortion. Distortion is not eliminated by neither ordinary grinding nor ordinary polishing. Single surface polishing comprises the steps of sticking a wafer upon a polishing disc on a reverse side, bringing the polishing disc into contact with a whetting cloth covering a polishing turntable, pressing the polishing disc to the turntable, supplying polishing liquid, rotating the polishing disc and revolving the turntable in reverse directions. The object bottom surface of the wafer is whetted by the polishing cloth glued to the turntable. When the wafer is stuck to a flat bottom of the polishing disc before polishing, the wafer is flattened. When the wafer is removed from the flat disc after polishing, the wafer deforms back to the original distortion. Distortion of a wafer is not eliminated by polishing but survives the polishing. It is impossible to rid a wafer of distortion by the ordinary polishing. Large wafer distortion increases difficulties in wafer process and enhances

probability of breaking, splitting and cracking. The wafer distortion makes it difficult to adjust a focus on the wafer in the masked exposure in photolithography and increases errors of patterning.

Simultaneous double surface polishing is composed of the steps of
5 preparing a template having a plurality of round holes, laying the template on a lower turntable with a whetting cloth, putting object wafers on the lower turntable in the holes of the template, lowering an upper turntable onto the lower one, pressing the object wafers between the upper and lower turntables, supplying whetting liquid, rotating the upper and lower turntables in reverse
10 directions and giving a planetary motion to the template. A top and bottom surfaces of the object wafers are polished simultaneously by the upper/lower turntables. When the wafers are picked up from the polishing machine, the wafers deform into the original distortion. Also in the double polishing, the distortion and inner stress survive the polishing. In general, lapping
15 (grinding) and polishing (whetting) are ineffective for reducing or removing distortion from wafers. Polished or lapped wafers recover the original deformation. Annihilation of distortion is a formidable problem for GaN wafers.

Another problem is fluctuation of thicknesses of wafers. Thickness
20 variations induce fluctuation of properties of devices produced on the wafer. Thickness should be constant in the overall area of a wafer for avoiding fluctuation of properties of devices. Suppression of the thickness fluctuation is another significant matter. There are several different kinds of estimation of the thickness fluctuation.

25 Here, a parameter TTV (total thickness variation) is adopted for

expressing the fluctuation of thickness. The TTV is, in short, a difference between the largest thickness and the smallest thickness among defined sampling points. The TTV is obtained by mounting an object wafer on a flat stage with a vacuum chuck, pulling one surface flatly on the stage, measuring heights of the other surface at sample points two-dimensionally-aligning at a predetermined spatial sampling period, deducing the maximum thickness and minimum thickness on the whole object wafer, and subtracting the minimum from the maximum. The TTV depends upon the spatial period d of measuring spots. The spatial period d which is a distance between neighboring spots can be arbitrarily determined. For example, $d=5\text{mm}$ is available. Otherwise, $d=1\text{mm}$ or 0.5mm is also available. A suitable spatial (sampling) period d should be defined by taking account of a texture of surfaces, size of wafers and required accuracy. The TTV is a value which is obtained by subtracting the smallest thickness from the largest thickness.

The TTV is not microscopic fluctuation of thickness but macroscopic difference between the maximum and the minimum. Thus, the TTV is essentially a macroscopic value, although thickness should be measured at many spots aligning in a two-dimensional lattice at a constant interval. Actual values of the TTV may slightly differ for different spatial periods d for the same specimen. A decrement of the sampling period d increases measured TTV. But, the TTV would uniformly converge at a definite value TTV_0 at an infinitesimal limit of $d \rightarrow 0$. Smaller d gives more precise value of TTV_0 but takes more time to measure heights at all sampling points. Here, $d=0.1\text{mm}$ is adopted. Surface heights are measured at sampling spots which are two-dimensionally aligned in a lattice at the sampling period

d=0.1mm. Then, TTV is obtained by subtracting the minimum from the maximum.

Another problem is roughness of wafer surfaces. At present top surfaces of GaN wafers are mirror-polished but bottom surfaces are
5 roughened. Difference of roughness discriminates the top from the bottom. The top surface should be mirror-smooth, because devices are fabricated upon the top by lithography. Since devices are not built upon the bottom surface, the roughened texture is allowable for the bottom surface. The inventors of the present invention are aware that a rough bottom surface incurs some
10 problems. In the case of prevalent Si wafers, GaAs wafers and InP wafers, a final washing step eliminates fine particles adhering to top and bottom surfaces by oxidizing and reducing the surfaces of the wafers. The elimination of particles from surfaces is called "lift-off". The oxidization/reduction treatment succeeds in removing particles from wafer
15 surfaces of Si, GaAs and InP which are chemically active and subject to oxidization. GaN is chemically more stable and more inactive than Si, GaAs and InP. GaN prevents a final washing step from lifting-off particles by oxidizing and reducing GaN surfaces with wet etchants. Rugged surfaces are far more likely to absorb and hold particles than smooth surfaces. If fine
20 particles once stick to rugged bottom surfaces of GaN wafers, it is very difficult to remove the particles from the rugged surfaces. Roughened bottom surfaces of current GaN wafers, in particular, are apt to wear many fine particles which are tiny fragments of polishing material, wax or others. The final washing step allows some of the particles to remove from the
25 bottom and to adhere to the top surface. Fig.11, which has an abscissa of

bottom surface roughness and an ordinate of top surface particle numbers, denotes that an increase of bottom surface roughness invites a conspicuous rise of particle numbers on the top surface.

Fig.11 indicates the requirement of decreasing the bottom roughness for
5 reducing contamination of top surfaces.

GaN freestanding bulk crystals are rigid but fragile. GaN lacks toughness unlike Si or GaAs. The rigid-fragility of GaN incurs another problem deriving from distortion. If a GaN wafer is strongly distorted, polishing steps are likely to induce occurrence of cracks originating from
10 convex/concave extremes of the distortion. Fig.3, which has an abscissa of curvature radii and an ordinate of crack occurrence rates, shows that stronger distortion with a shorter radius yields a higher rate of occurrence of cracks. Fig. 3 requests reducing distortion of wafers for avoiding occurrence of cracks.

15 SUMMARY OF THE INVENTION

A purpose of the present invention is to provide a freestanding nitride semiconductor wafer which ensures good morphology of films epitaxially grown on the nitride wafer. Another purpose of the present invention is to provide a freestanding nitride semiconductor wafer which is endowed with
20 high yield of via-mask exposure in photolithography. A further purpose of the present invention is to provide a nitride semiconductor wafer which has a top surface with low probability of particle contamination in wafer processes. Another purpose of the present invention is to provide a gross-polishing method for reducing inherent distortion of nitride wafers. A further purpose
25 of the present invention is to provide a chemical/mechanical polishing method

for polishing rigid/fragile nitride semiconductor wafers into mirror-smoothness without fear of breaks.

The present invention proposes a freestanding nitride semiconductor wafer having maximum distortion height H_m less than $12\mu\text{m}$ irrespective of having one, two, three or any other number of mode of distortion. The restriction $H_m \leq 12\mu\text{m}$ is required for all wafers bent in any modes of distortion.

The words of "modes of distortion" are yet ambiguous. Distortion should be described by maxima, minima and numbers of maxima and minima. For example, when a wafer has more than two maxima $T_1, T_2, T_3 \dots$ and more than two minima $K_1, K_2, K_3 \dots$ in the diametrical direction or in the angular direction, the wafer bends in saddle-point type distortion. Even in such cases, the distortion height H can be exactly defined by keeping all the minima in contact to a flat plane, measuring heights of all the maxima and taking the maximum of the measured heights. In the complex distortion also, the present invention requires the fundamental inequality $H_m \leq 12\mu\text{m}$.

More favorable distortion height is $H_m \leq 5\mu\text{m}$ in the present invention. Distortion less than $5\mu\text{m}$ still further improves morphology of epitaxial films piled on a wafer, enhances the yield of the via-mask exposure in photolithography and succeeds with a higher rate in preventing cracks from occurring in wafer processes.

When a wafer has a single maximum T_1 , the wafer is bent in a single-mode distortion as shown in Fig.6(1). In the single-mode distortion, H and R can be related with each other by a simple equation which will be later described. In the case of a $45\text{mm}\phi$ wafer, a distortion height $H=12\mu\text{m}$

corresponds to a curvature radius $R=21\text{m}$. Although the restriction defined by the peak height is valid for any diameter or any distortion mode, the restriction defined by the minimum curvature radius depends upon radii and modes of distortion. Here, restrictions of a curvature radius R for a
5 45mm ϕ wafer, which is the minimum diameter proposed by the present invention, are described. Then, the curvature radius R of distortion should be longer than 21m for a 45mm ϕ wafer ($R\geq 21\text{m}$). The optimum restriction $H\leq 5\mu\text{m}$ means $R\geq 50\text{m}$ in the case of a 45mm ϕ wafer ($R\geq 50\text{m}$).

In the case of a single-mode distortion, the present invention requires
10 that the distortion height H_m should satisfy inequalities,

(1) $H_m\leq 12\mu\text{m}$ in the case of 45mm ϕ , in general, $R\geq 21\text{m}$.

More favorably,

(2) $H_m\leq 5\mu\text{m}$ in the case of 45mm ϕ , in general $R\geq 50\text{m}$.

The restriction defined by H_m depends upon the size of the object
15 wafer. Otherwise, the condition expressed by curvature radius R is common for any size of wafers. Restrictions by R and H_m are equivalent only for 45mm ϕ wafers. The maximum height requirements $H_m\leq 12\mu\text{m}$ and more favorable $H_m\leq 5\mu\text{m}$ are valid for a number of distortion peaks.

In many cases, GaN wafers are distorted in a single distortion mode,
20 which has a single extreme. In addition to the single distortion mode, double or thrice distortion mode happens at smaller rates. The double distortion sometimes has two maximum extremes and two minimum extremes align on a diameter. Instead of simple linear aligning extremes, more complex multiple-distortion mode has two pairs of maximum and minimum
25 extremes positioned at corners of a virtual square imagined on an object

wafer, in which all the four extremes form saddle points. In the saddle point mode, two minimum extremes and three maximum extremes align on a diameter and two maximums and three minimums align on another diameter.

Fig.10 shows a complex distortion of a wafer having three minimum extremes K1, K2 and K3 and two maximum extremes T1 and T2 on a diameter. This example happens to have five extremes aligning on a diameter. The four saddle point case mentioned above has a section of three modes of distortion as shown in Fig. 10. In this case, a three distortion mode has peak points K1, K2 and K3. If the three mode case should have a common allowable distortion height H, the allowable curvature radius R of the three distortion mode should be far smaller than the simple single distortion.

The three mode distortion decreases the size of a deforming area to one third ($1/3$) of the single mode. The allowable curvature radius decreases to one ninth ($1/9$) of the single mode case. In the three-mode distortion, an allowable curvature radius R should be longer than 2.3m, since the height H should be less than $12\mu\text{m}$ ($R \geq 2.3\text{m}$ for $H \leq 12\mu\text{m}$). More favorably, a curvature radius should be larger than 5.6m for the restriction of $H \leq 5\mu\text{m}$ ($R \geq 5.6\text{m}$ for $H \leq 5\mu\text{m}$).

Instead of the pressed top turntable of the conventional polishing, the present invention adopts a non-pressing top turntable and distorted wafers in a no weight-polishing by pulling up the top turntable with a force nearly equal to the weight of the upper turntable. The polishing machine allows the upper and lower turntables to make a air gap which is wider than a thickness of a wafer. Pressure P acting upon a wafer should be less than $60\text{g}/\text{cm}^2$ for the present invention ($P \leq 60\text{g}/\text{cm}^2$). $60\text{g}/\text{cm}^2$ means 60g weight acting upon a

unit area of 1cm^2 . Here, g/cm^2 is not an MKS SI(international system) unit but a practical technological unit. There are many different units for signifying pressure. The same critical pressure as $60\text{g}/\text{cm}^2$ should be expressed in other units.

5 $P = 60\text{g}/\text{cm}^2 = 0.06\text{kg}/\text{cm}^2 = 60\text{g} \times 980\text{cm}/\text{sec}^2 \times 1/\text{cm}^2 = 58800\text{dyn}/\text{cm}^2$
 $= 5880\text{N}/\text{m}^2 = 5880\text{Pa} = 44.1\text{Torr} = 58.8\text{mbar} = 0.0580\text{atm}.$

Since normal polishing presses an object at several of kg/cm^2 , the above $60\text{g}/\text{cm}^2$ is very small pressure which is effectively zero. The state of pulling up the upper turntable ($P \leq 60\text{g}/\text{cm}^2$) is called "pressureless". What
10 features this invention is pressureless polishing which polishes a wafer in a quasi-free state.

Instead of pressing down the upper turntable, the present invention lifts up the upper turntable for gross-polishing an object wafer. A wide air gap is kept between the upper and lower turntables. The air gap is wider than the net
15 thickness of the wafer but narrower than the distorted thickness of the wafer. The air gap allows the wafer to keep the inherent distorted shape in a quasi-free state.

Since the wafer is bent between the upper and lower turntables, protrusion portions and sharply edging portions keep contact with the
20 polishing clothes on the turntables. Concave parts are separated from the polishing clothes. Only the protruding and the edging portions are eliminated but concave recesses are left untouched. The projecting portions and edging portions are decreased, which indicates decrement of distortion.

After a long time polishing, flat wafers without distortion are obtained
25 by the free-state polishing of the present invention. The free-state polishing

enables the present invention to eliminate any mode of distortion, e.g., double-mode, triplet-mode or other higher mode of distortion (Fig.10) of nitride wafers in addition to the simple single-mode distortion as shown in Fig.5. The polishing method takes much time but is effective for removing
5 inherent distortion of nitride wafers. The problem of distortion of nitride wafers is solved by the present invention.

Another important property is surface roughness. The present invention requires that a roughness RMS of a top surface of nitride wafers should be less than 5nm. The lower limit is 0.1nm, which derives from the
10 restriction of the technology of polishing of the present invention. The RMS is a root mean square of heights. There are Rmax, Ra and other parameters for signifying the roughness. Here, the present invention employs the RMS for representing the roughness. The roughness of the top is thus represented by $0.1\text{nm} \leq \text{RMS} \leq 5\text{nm}$.

15 The conventional GaN wafers have never been polished up to such smoothness, since no CMP (chemical/mechanical polishing) was available. As explained before, since nitride crystals are rigid and fragile, mechanical polishing alone cannot produce mirror smoothness of nitride wafers yet. Success of the CMP enables the present invention to give such high
20 smoothness to surfaces. The CMP will be described later in detail.

Fig.1 shows a relation between surface morphology after epitaxial growth and surface roughness or TTV(total thickness variation). Greater roughness induces a decline of morphology of an epitaxial wafer which has epitaxially grown films upon the bare GaN wafer having ragged surfaces.
25 Fig.1 indicates that epitaxial films have a tendency of transcribing the

roughness of the substrate wafer and smoothness of wafer surfaces is important for making good epitaxial films.

More favorable smoothness of the top surface is defined to be less than 0.5nm. Thus, the preferable requirement can be represented by
5 $0.1\text{nm} \leq \text{RMS} \leq 0.5\text{nm}$.

The single crystal nitride semiconductor wafer of the present invention should have a bottom of roughness lower than $\text{RMS} 5000\text{nm}$, which is far smaller than the current bottom roughness. The minimum of the roughness of the bottom should be 0.1nm which is a technical limit of polishing. Thus,
10 the bottom surface roughness RMS of the present invention can be briefly expressed by an inequality $0.1\text{nm} \leq \text{RMS}(\text{bottom}) \leq 5000\text{nm}$.

Fig.11 shows a tendency of an increase of a top surface particle number as bottom roughness rises. It is because the particles once adhering to the bottom separate from the bottom, turn around and contaminate the top. This
15 invention can decrease the adhesion of particles on the top since the bottom has a smooth surface of small roughness. The above-mentioned CMP is effective to the bottom polishing.

In brief, the present invention requires that both surfaces should have the following roughness,

20 [General requirements]

top surface roughness $0.1\text{nm} \leq \text{RMS} \leq 5\text{nm}$

bottom surface roughness $0.1\text{nm} \leq \text{RMS} \leq 5000\text{nm}$

[More sophisticated requirements]

top surface roughness $0.1\text{nm} \leq \text{RMS} \leq 0.5\text{nm}$

25 bottom surface roughness $0.1\text{nm} \leq \text{RMS} \leq 2\text{nm}$

A freestanding single crystal nitride semiconductor wafer of the present invention has a diameter larger than 45mm ϕ and a TTV (total thickness variation) less than 10 μ m in the case of a 45mm ϕ wafer in addition to the above-described roughness and distortion.

5 Here, the relation between the height H and the curvature radius R of distortion is described in short. Fig.9 shows a relation between a central wafer height H and a curvature radius R which are different expressions of distortion of wafers in a simple mode. A diameter of a wafer is denoted by FMG. The diameter D of the wafer FMG is FG (D=FG). Curvature FMG is
10 a part of a large sphere which has a center O. The distortion FMG has a curvature radius R=OF=OM=OG. The central height H is equal to MN (H=MN). The wafer diameter D satisfies an equation of $D = FG = 2R\sin\Theta$. As Θ is a small angle, $D = 2R\Theta$ in approximation.

The height H satisfies $H = MN = MO - NO$. $MO = R$ and $NO =$
15 $OG\cos\Theta = R\cos\Theta$. The height H is given by

$$H = R - R\cos\Theta = 2R\sin(\Theta/2)^2 = D^2/8R. \quad (1)$$

This is an approximation equation for determining the relation between H and R. Since D/R is far smaller than 1, the approximation is a good one. The curvature radius R is reversely proportional to H. This relation equation
20 includes the wafer diameter D as a parameter. A proportion constant includes a square of the diameter D. Unless D is determined, the relation is not fully decided. The present invention aims at a wafer which is larger than 45mm ϕ ($D \geq 45\text{mm}$). If R should be denoted by a meter unit and H should be signified in μ m (micrometer) unit, Equation (1) is written as

25 For $D=45\text{mm}$ $R = 253/H.$ (R;m and H; μ m) (2)

For $D=50\text{mm}$ $R = 312/H$. ($R;\text{m}$ and $H;\mu\text{m}$) (3)

In the case of a 2 inch wafer ($D=50\text{mm}$), a curvature radius $R=26\text{m}$ gives a height $H=12\mu\text{m}$. A curvature radius $R=62\text{m}$ gives $H=5\mu\text{m}$ for $D=50\text{mm}$.

5 In the case of $45\text{mm}\phi$ wafers, the present invention can determine a distortion curvature R (denoted by a m unit) larger than $D^2/96$ (denoted by a mm unit) from the above equation (1).

The present invention restricts an allowable distortion height H to be less than $12\mu\text{m}$ ($H\leq 12\mu\text{m}$). $H=12\mu\text{m}$ is the maximum of allowable distortion
10 heights. Thus, in the case of a $50\text{mm}\phi$ wafer, the minimum allowable curvature R_{m} is $R_{\text{m}}=26\text{m}$ and curvature R and height H should satisfy inequalities $R\geq 26\text{m}$ and $H\leq 12\mu\text{m}$. Although the allowable maximum H is common, the minimum curvature radius R_{m} depends upon the wafer diameter D . For a $45\text{mm}\phi$ wafer, $H\leq 12\mu\text{m}$ or, equivalently, $R\geq 21\text{m}$.

15 More preferable height should be less than $5\mu\text{m}$ ($H\leq 5\mu\text{m}$) in the present invention. For maintaining H at a value less than $5\mu\text{m}$, $R\geq 62.5\text{m}$ for $D=50\text{mm}$ and $R\geq 50.6\text{m}$ for $D=45\text{mm}$.

In the case of a uniform distortion as shown in Fig.6(1), as a curvature radius R of distortion rises, a mask/resist exposure yield in photolithography
20 improves. Namely, a smaller height H and a larger radius R are favorable for making devices with higher yield. It is important to reduce distortion. The present invention requires that the distortion should be suppressed at most to be a $12\mu\text{m}$ height.

Distortion necessarily accompanies any freestanding GaN single crystal
25 which has been made in vapor phase upon a foreign material (e.g., GaAs)

undersubstrate. The present invention gross-polishes (or laps) a wafer in a pressureless state. It takes long time to lap a distorted wafer in a quasi-free state. But the pressureless gross-polishing or lapping of the present invention succeeds in eliminating distortion from the object wafer down to
5 $H \leq 12 \mu\text{m}$ which is equivalent to $R \geq 26 \text{m}$ in the case of $50 \text{mm}\phi$ (2 inch) wafers or to $R \geq 21 \text{m}$ in the case of $45 \text{mm}\phi$. The present invention further recommends to reduce the distortion down to $H \leq 5 \mu\text{m}$ which is equivalent to $R \geq 60 \text{m}$ in the case of $50 \text{mm}\phi$, which takes still longer time than the standard of $H \leq 12 \mu\text{m}$.

10 Gallium nitride (GaN) is rigid but fragile. Rigidity/fragility is a drawback of GaN or other nitride semiconductors. Application of strong pressure causes breaks of wafers in polishing process. The fragility prohibits mechanical polisher from applying strong pressure upon a nitride wafer. Mechanical polishing making use of silicon carbide, alumina or
15 diamond powder cannot finish nitride wafers into mirror smoothness due to the restricted pressure application. GaN has longed for chemical-mechanical polishing which would dispense with strong pressure application.

GaN is chemically inactive. It has been believed that chemical-mechanical polishing is impossible for GaN. The inventors of the
20 present invention examined various alkalis, acids or other chemicals for seeking probability of CMP of GaN. The inventors finally found out a probability of the GaN CMP by potassium peroxodisulfate ($\text{K}_2\text{S}_2\text{O}_8$) and ultraviolet rays. Potassium peroxodisulfate has strong oxidizing power. GaN is resistant to potassium peroxodisulfate itself. Potassium
25 peroxodisulfate is not corrosive to GaN. Irradiation of ultraviolet rays,

however, enhances the action of potassium peroxodisulfate. Ultraviolet-excited potassium peroxodisulfate strengthens oxidizing power. The inventors discovered that ultraviolet rays enable potassium peroxodisulfate and polishing powder (e.g., colloidal silica) to chemically
5 polish GaN crystals. It turns out that silicon carbide, alumina or diamond powder is also effective as polishing powder in addition to the colloidal silica. This is the first success of CMP of GaN. The ultraviolet-enforced potassium peroxodisulfate chemical/mechanical polishing is useful for both rough-polishing and minute-polishing. A set of polishing powder, potassium
10 peroxodisulfate and ultraviolet rays enables the inventors to chemical-mechanical polish rigid but fragile GaN wafers up to sufficient mirror smoothness with small pressure. The ultraviolet-excited potassium peroxodisulfate has strong corrosive power for chemically high resistant GaN. Chemical corrosion prepares active surfaces and helps powder granules to
15 polish GaN wafers physically at low pressure. Since applied pressure is weak enough, fragile GaN wafers do not break. The inventors further confirmed that the ultraviolet-enhanced potassium peroxodisulfate with polishing granules is effective for polishing other nitride semiconductors, AlGa_N, AlN and InN.

20 The conventional GaN wafers had a roughened bottom surface which is likely to attract particles and allow them to adhere thereon. The present invention polishes also a bottom surface into mirror smoothness. A smoothed bottom surface of a nitride wafer of the present invention is immune from particle contamination. Reduction of the particle
25 contamination is an advantage of the present invention. Another advantage

derives from small TTV (total thickness variation) less than $10\mu\text{m}$ ($\text{TTV} \leq 10\mu\text{m}$). The thickness of the wafer is nearly constant all over on the surface. The small TTV can suppress the fluctuation of properties of devices made upon the wafers. For example, surface morphology after epitaxial film-growth is improved by the low fluctuation of thickness (TTV) realized by the present invention.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig.1 is a graph of a relation between morphology of a GaN wafer after epitaxial growth and TTV(total thickness variation) or roughness RMS(μm) for showing that an increase of the TTV or RMS degrades surface morphology of the wafer piled with epitaxial thin films thereon.

Fig.2 is a graph denoting a relation between a yield of mask exposure wafers in photolithography and a curvature radius of distortion R(m) for showing that large wafer distortion lowers the yield of mask-exposed wafers. The ordinate is the yield. An upward direction denotes better yield and a downward direction denotes worse yield.

Fig.3 is a graph of a relation between an occurrence rate of cracks in wafer-process and a curvature radius of distortion R(m) for showing that large distortion causes cracks on processed wafers.

Fig.4 is a flow chart of processing as-grown GaN wafers into mirror wafers including the steps of rough shaping an anomalous disc into a circular one, bevelling or chamfering of peripheries, gross-polishing for eliminating distortion, minute (second) polishing for producing mirror smooth surfaces, washing and testing.

Fig.5 is a schematic sectional view of a part of a gross-polishing

machine for showing pressureless polishing which pulls up the upper turntable, maintains a distorted state of an object distorted wafer and eliminates protruding portions and edgy portions.

Fig.6 is a set of sectional views of a wafer being processed by the pressureless gross-polishing step which lifts up an upper shaft for keeping the distorted state of the wafer.

Fig.7 is a sectional view of a pressureless gross-polishing machine which eliminates distortion from deformed wafers by inserting the distorted wafers in holes of templates on a lower turntable, putting an upper turntable above the lower turntable with a sufficient air gap, and revolving the turntables without pressing the wafers.

Fig.8 is a sectional view of a CMP machine which polishes a GaN wafer by supplying a chemical/mechanical polishing liquid including potassium peroxodisulfate ($K_2S_2O_8$), potassium hydroxide (KOH) and colloidal silica and irradiating by ultraviolet rays for making mirror smooth wafers without occurrence of breaks and scratches.

Fig.9 is an explanatory figure for clarifying a relation of a wafer central height (H) of a diameter (D) and a curvature radius (R) for signifying distortion of a wafer.

Fig.10 is a section of a triplet-bending mode wafer having two maxima T1 and T2 and three minima K1, K2 and K3 along a diameter.

Fig.11 is a graph of a relation between bottom roughness RMS(μm) and top particle number showing that an increase of the bottom roughness induces a rise of the number of particles lying on the top surface. The abscissa is bottom surface roughness RMS(μm). The ordinate is particle numbers on the

top surface after wafer processes.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Since there have been rare freestanding circular GaN wafers till now, processing of as-grown GaN wafers has not been established at present.

5 Then, the inventors treated GaN circular wafers by a series of steps as shown in Fig.4. The processing treatment comprises rough shaping, bevelling (or chamfering), gross polishing, minute polishing, washing and testing steps. An as-grown GaN is not circular. The rough shaping step reforms the as-grown wafer into a circular one. The chamfering step grinds the
10 circumference into slanting edges for avoiding occurrence of breaks or splitting. Improvement of the following gross and minute polishing steps is a purpose of the present invention.

The polishing is done step by step by changing the size of powder. The polishing processes can be divided into the first (gross) polishing at a higher
15 speed and the second (minute) polishing at a slower speed. Another role of the first polishing is to rid the wafer of the distortion. The second polishing is now done by a new CMP method contrived by the inventors of the present invention. Both kinds of polishing are described in detail.

Ordinary rough polishing for Si or GaAs wafers makes use of a round
20 plate having a shaft for fixing a wafer on a side, pushes the round plate upon a lower turntable, revolves the turntable and rotates the round plate around the shaft. Even if the object wafer has inherent distortion, fitting the wafer upon a flat plate evens the wafer. The wafer is uniformly polished in a flattened state under strong pressure. When the polished wafer is taken off
25 from the plate, the wafer retrieves the inherent distortion. The distortion

remains intact. The ordinary single-side polishing is ineffective for reducing distortion. The present invention takes weightless, pressureless gross polishing with very small pressure less than 60g/cm^2 in quasi-free state for alleviating distortion by eliminating only protruding, edging portions.

5 The pressureless polishing sandwiches a distorted wafer between lower and upper turntables in a bent state and whets the distorted wafer slowly without pressing down. The upper turntable is not pressed down but lifted up for keeping a wide air gap between the upper and lower turntables, which allow the wafer to bend in the inherent distortion.

10 Fig.5 is a schematic view of a weightless polishing of the present invention for gross-polishing a deformed GaN circular wafer. A polishing machine has a coaxial set of an upper turntable 3 and a lower turntable 4 which can rotate, rise and sink. A distorted wafer 2 is freely sandwiched between the lower turntable 4 and the upper turntable 3 with a wide air gap.

15 The wafer is not stuck to a polishing disc which is prevalently used for wafer polishing. Polishing discs are useless, because the polishing discs hold a wafer in a forced flattened state. Both the upper and lower turntables are metallic turntables coated with polishing cloths. A polishing liquid is supplied between the upper and lower turntables. The upper and lower

20 turntables rotate in the reverse direction or in the same direction at different rotation velocities for gross-polishing an object wafer in a distorted state. The polishing liquid includes water and free whetting granules, for example, silicon carbide (SiC), alumina (Al_2O_3) or diamond (C) granules. Unlike an ordinary polishing machine, the upper turntable 3 is not pressed down but is

25 lifted upward. Lifting up of the upper turntable 3 makes an air gap which is

wider than a net thickness of an object wafer. The object wafer exists between two turntables in a free distorted state. In the example, a bottom circumference η or λ touches the lower turntable 4 and a top γ center is in contact with the upper turntable 3.

5 Fig.6 shows sections of a distorted wafer at various steps of the pressureless, weightless, quasi-free gross-polishing of the present invention for eliminating distortion from the object distorted GaN wafer. At first the object wafer has a single-mode distortion with a center upward bending and a periphery downward bending. Fig.6(1) denotes a free state of the wafer. A
10 top convex curve, a left side, a bottom concave curve and a right side are designated by $\alpha\beta\gamma\delta\epsilon\zeta\theta\iota\kappa\lambda\nu$. The wafer is upward convex at the beginning step. The pressureless polishing allows the wafer to distort in a free state. A protruding central top γ is in contact with a polishing cloth of an upper turntable and edging bottom peripheries λ and η touch a polishing cloth of a
15 lower turntable. Other portions are left intact. Only the protruding top γ and the edging η and λ are polished away. As shown in Fig.6(2), a flat round top $\beta\delta$ and flat fringes $\sigma\pi$ and $\rho\sigma$ are created by the weightless polishing at the second step. Lower top portions $\alpha\beta$ and $\delta\epsilon$ and a concave bottom part $\theta\iota\kappa$ is left untouched. The polishing continues by gradually
20 lowering the upper turntable for maintaining partial contact with the top of the wafer. The pressureless polishing is widening the top flat part $\xi\tau\nu$ and the bottom flat annular fringes $\phi\chi$ and $\psi\omega$, as shown in Fig.6(3). At a final step, top lower circumferences $\epsilon\nu$, $\xi\alpha$ and a bottom concave $\theta\iota\kappa$ are polished away. A flat wafer having a flat top $\mu q s$ and a flat bottom $\zeta t y z v$ is obtained
25 as shown in Fig.6(4).

Fig.5 shows a principle of the pressureless polishing for a single wafer on the teaching of the present invention. Actually, a plurality of wafers are simultaneously polished at both surfaces in a planetary motion in a polishing machine.

5 Fig.7 shows a structure of a gross-polishing machine which polishes a plurality of wafers in a pressureless state. The polishing machine are not novel. But, a relation among upper, lower turntables, a template and wafers is novel. An upper turntable 3 faces downward a lower turntable 4. Polishing cloths 5 and 6 are glued to the turntables 3 and 4. The upper
10 turntable 3 is rotated by an upper driving shaft 26. The lower turntable 4 is rotated by a lower driving shaft 27. Two turntables rotate around a common axial line. The upper turntable 3 can be lifted up and can be maintained at an arbitrary height for making an air gap between the upper and lower turntables.

15 The machine has a sun gear 20, a plurality of templates 22 with an outer-toothed planetary gear meshing with the sun gear 20 and an outer internal gear 23 meshing with the template 22 between the upper turntable 3 and the lower turntable 4. The central sun gear 20 and the outer internal gear 23 rotate in inverse directions. The templates 22 are thin plastic discs
20 having a plurality of round holes 25 for holding circular wafers 2. The templates 22 are thinner than the wafers. Tops and bottoms of the wafers 2 are in contact with the upper and lower turntables. When m templates having n holes are employed, nm wafers can be treated at a time. The templates 22 revolve around the main axis and rotate around a center of the
25 holes in a planetary motion.

A polishing liquid should be supplied between the upper and lower turntables. As mentioned before, mechanical polishing and chemical/mechanical polishing are available for the first (gross) polishing. Here, the first polishing employs a pure mechanical polishing. Then, the polishing liquid includes polishing powder and a liquid for dispersing the powder and for obtaining a lubricating property. In the case of mechanical polishing, the liquid is water or the like for dispersing powder granules. In the case of chemical/mechanical polishing, the liquid should include the above-described potassium peroxodisulfate. Rough polishing (first polishing) is here a mechanical polishing making use of silicon carbide (SiC), alumina or diamond granules dispersed in the liquid. In Fig.7, wafers 2 held in the holes 25 of the template 22 are gross-polished by supplying the polishing liquid between the turntables, and rotating the sun gear 20 at an angular velocity Ω_s , the internal gear 23 at an angular velocity Ω_i , the upper turntable 3 at an angular velocity Ω_u and the lower turntable 4 at an angular velocity Ω_d , where the definition of the angular velocities include directions and counterclockwise rotations are determined to be positive. The sun gear 20 has a shaft extending upward or downward to a motor. The motor rotates the sun gear. The upper and lower turntables are revolved by the upper and lower shafts 26 and 27. The upper turntable 3 can be revolved either in the same direction or in the reverse direction to rotation of the lower turntable 4. The internal gear 23 can be also revolved by another motor at an arbitrary rate. Here, S, P and I denote tooth numbers of the sun gear, the planetary gear and the internal gear. The tooth numbers satisfy a relation of $S + 2P = I$.

I. A revolving velocity Ω_c of the template 22 is ruled by an equation of $S\Omega_s$

+ $I\Omega_i = (S+I)\Omega_c$. A planetary rotating velocity Ω_c of the template (planetary gears) and a rotation velocity Ω_i of the internal gear satisfy $P\Omega_t = I\Omega_i$. Arbitrary rotation speed Ω_t and revolving speed Ω_c are realized by adjusting Ω_u , Ω_d , Ω_s and Ω_i which are all independent controllable parameters. Such
5 a structure is favorable for remedying inherent distortion in accordance with the teaching of the present invention, because the machine need not fix an object wafer on a flat disc on one side.

What is significant in the machine in Fig. 7 is the upper turntable 3 being pulled upward by force F , air gaps being formed, and wafers being
10 gross-polished in a free-distorted state in the air gaps. Projecting portions, e.g., bottom edgy peripheries and protruding top centers in the example, are polished but concave portions, e.g., bottom recesses and lower top peripheries, which are not in contact with the turntables, are not polished. Maintaining small area contact and small pressure with the wafers, the upper turntable 3 is
15 gradually descended. Protrusions and edges are all polished away. Extra parts which protrude beyond an imaginary flat disc are eliminated. The distortion of the wafers are essentially removed by the pressureless polishing. Finally, flat, distortion-free wafers are obtained by the free-state gross polishing.

20 The wafers should be further treated by a second (minute) polishing for making mirror wafers. The chemical/mechanical polishing should be employed for the minute polishing for enhancing flatness and smoothness of surfaces without applying excess high pressure. Fig.8 shows the CMP fine polishing which supplies a mixture liquid 9 including powder, potassium
25 hydroxide (KOH) and potassium peroxodisulfate ($K_2S_2O_8$) between the upper

and lower turntables, and irradiates the liquid with ultraviolet rays. The composition of the polishing liquid, the polishing powder and the ultraviolet ray source are as follows.

Polishing liquid 2M KOH (potassium hydroxide)

5 0.5M $K_2S_2O_8$ (potassium peroxodisulfate)

Polishing granules colloidal silica: granule size = 50nm ϕ to 450nm ϕ

best size = 200nm ϕ

Ultraviolet ray source mercury lamp (Hg): wavelength $\lambda=254\text{nm}$

power $P = 10\text{mW/cm}^2$

10 As a polishing liquid of the second polishing step, the present invention can employ a polishing liquid including potassium hydroxide from 0.5M to 4M, potassium peroxodisulfate from 0.2M to 2M and polishing powder. The potassium peroxodisulfate is known as an oxidizing material. As described before, people have believed that it is impossible to
15 chemical/mechanical-polish GaN which is chemically resistant. The inventors of the present invention found out that the ultraviolet-excited potassium peroxodisulfate enables us to CMP-polish GaN crystals. Potassium peroxodisulfate itself is inactive to GaN. But, ultraviolet rays enhance oxidization power of the potassium peroxodisulfate and give the
20 potassium peroxodisulfate corrosive action to GaN.

The present invention has succeeded in CMP of GaN by the use of ultraviolet-enhanced potassium peroxodisulfate and polishing granules (e.g., colloidal silica) for the first time. The CMP can finish rigid but fragile nitride semiconductor wafers into mirror smoothness of $0.1\text{nm}\leq\text{RMS}\leq 5\text{nm}$
25 without strong pressure. Without potassium peroxodisulfate, polishing

granules (e.g., colloidal silica) cannot solely polish the GaN wafer into mirror smoothness. The potassium peroxodisulfate plays a main role of polishing.

What determines the final smoothness is, however, the size of polishing granules. The surface roughness can be raised by changing sizes of granules step by step. Larger diameter granules polish more rapidly than smaller diameter granules. Smaller diameter granules can finish wafers into higher smoothness than larger diameter granules. For example, in the case of colloidal silica, sizes of granules should be varied from 450nm ϕ to 50nm ϕ .

The sizes of granules rule the speed and the final roughness. But, what enables the granules to polish nitride wafers is the potassium peroxodisulfate. Another factor which determines the final roughness is time. It takes longer time to obtain more smoothly finished surfaces. RMS = 0.1nm is a lower limit originating from technical restrictions. The above written $0.1\text{nm} \leq \text{RMS} \leq 5\text{nm}$ is sufficient smoothness to a top surface. Surface morphology of the films grown epitaxially upon the top surface of $0.1\text{nm} \leq \text{RMS} \leq 5\text{nm}$ is satisfactory. However, $0.1\text{nm} \leq \text{RMS} \leq 0.5\text{nm}$ is still better for the top surface roughness.

In the case of a bottom surface, $0.1\text{nm} \leq \text{RMS} \leq 5000\text{nm}$ of smoothness is allowable. $\text{RMS} \leq 5000\text{nm}$ is enough for the bottom surface to maintain a top surface being immune from contamination of particles. But, $\text{RMS} \leq 2\text{nm}$ is more favorable for the roughness of the bottom surface.

[General requirements]

top surface roughness $0.1\text{nm} \leq \text{RMS} \leq 5\text{nm}$

bottom surface roughness $0.1\text{nm} \leq \text{RMS} \leq 5000\text{nm}$

[More favorable requirements]

top surface roughness $0.1\text{nm}\leq\text{RMS}\leq0.5\text{nm}$

bottom surface roughness $0.1\text{nm}\leq\text{RMS}\leq2\text{nm}$

[EMBODIMENT 1 (2-inch ϕ GaN freestanding wafer)]

2-inch ϕ GaN freestanding wafers are made by an HVPE method which
5 grows GaN films on a GaAs circular undersubstrate from a Ga-melt, HCl gas
and NH₃ gas in a furnace by reactions of $\text{Ga}+\text{HCl}\rightarrow\text{GaCl}$ and $\text{GaCl}+\text{NH}_3\rightarrow$
GaN. The HVPE method makes the best use of the ELO (epitaxial lateral
overgrowth) and the facet-growth which produces intentionally facet pits for
gathering dislocations at bottoms of the pits and eliminates the GaAs
10 undersubstrate and obtains a low-dislocation freestanding thick GaN film.

As-HVPE-grown GaN bulk wafers have rugged surfaces, random
peripheral fringes, distortion and fluctuation of thickness. The
rough-shaping step of Fig.4 reforms the as-grown wafers into circular wafers
by eliminating the random peripheral fringes.

15 The bevelling (chamfering) step of Fig.4 eliminates sharp edges at
circumferences of the circular wafers. Some of the prepared circular wafers
have single-mode distortion and others have triple-mode or larger mode of
distortion.

After the rough shaping and the chamfering, the pre-treated GaN
20 circular wafers are processed by two steps of polishing in accordance with the
teaching of the present invention.

[Conditions of gross-polishing]

The first (gross) polishing includes three steps using different sizes of
granules. Polishing liquids including SiC granules of various sizes are
25 employed.

Polishing liquid:

Powder: silicon carbide (SiC)

First step; average size $15\mu\text{m}$ (#800)

Second step; average size $6\mu\text{m}$ (#2500)

5 Third step; average size $2\mu\text{m}$ (#6000)

Liquid: oil slurry

Upper turntable: cast iron $380\text{mm}\phi$

Lower turntable: cast iron $380\text{mm}\phi$

Rotation speeds: upper-, lower-turntables: 20 to 60 rpm

10 Sun gear: 10 to 30 rpm

Internal gear: 0 to 10 rpm

Liquid supply: $500\text{ cm}^3/\text{min}$ (circulation)

Pressure: 30 to 60 g/cm^2

Polishing speed: first step $0.3\mu\text{m}/\text{min}$

15 second step $0.05\mu\text{m}/\text{min}$

third step $0.02\mu\text{m}/\text{min}$

Polishing margin: total 60 - $80\mu\text{m}$ (top + bottom)

Although silicon carbide (SiC) is utilized as a polishing powder of the first polishing step here, one of colloidal silica, alumina and diamond
20 powders with an average diameter of $20\mu\text{m}$ to $0.5\mu\text{m}$ can be suitably chosen. The first (rough-) polishing is done by sandwiching deformed wafers between the lower and upper turntables without pressure, polishing top and bottom surfaces at a slow speed and eliminating protruding portions and edges, as shown in Fig.5 and Fig.6. The inherent distortion of the wafer is removed
25 by the pressureless polishing. In practice, object wafers are allotted in holes

of templates, which make a planetary gear motion, and are maintained between the turntables. The polishing speeds are slow, which results from the pressureless polishing. The wafers after the free-state rough polishing have very small distortion or no distortion. Then, the wafers are treated by a
5 second (minute) polishing.

[Conditions of minute-polishing]

The second (minute) polishing is a chemical/mechanical polishing making use of ultraviolet-excited potassium peroxodisulfate.

Polishing liquid:

10 Powder: colloidal silica; average size $0.2\mu\text{m}$ (200nm)

Liquid: $\text{KOH} + \text{K}_2\text{S}_2\text{O}_8$

Ultraviolet rays: mercury (Hg) lamp $\lambda = 254\text{nm}$

Polishing cloth: nonwoven fabric

Upper turntable: cast iron $380\text{ mm}\phi$

15 Lower turntable: cast iron $380\text{ mm}\phi$

Rotation speeds: upper-, lower-turntables: 20 to 60 rpm

Sun gear: 10 to 30 rpm

Internal gear: 0 to 10 rpm

Liquid supply: $1000\text{ cm}^3/\text{min}$

20 A 2-inch ($50\text{mm}\phi$) wafer (A) polished by the processes has a single-mode distortion of $R=100\text{m}$. Roughness of the top surface and the bottom surface was measured by an AFM (atomic force microscope). The measured roughness was $\text{RMS} = 0.3\text{ nm}$ to 0.5 nm in a square of $10\mu\text{m} \times 10\mu\text{m}$ for both the top and the bottom surfaces. Although the top and bottom
25 surfaces cannot be discerned by the difference of roughness any more, a

G-plane is defined as a top surface and an N-plane is defined as a bottom surface.

The fluctuation of thickness was $TTV=3.5\mu m$ (measured at a 0.1 mm interval). The obtained distortion $R=100\text{ m}$ corresponds $H=3.5\mu m$ (for 5 50mm ϕ) which satisfies the prescribed restriction $H\leq 12\mu m$. The roughness ($RMS=0.3\text{nm}$ to 0.5nm) also satisfies the requirements $0.1\text{nm}\leq RMS\leq 5\text{nm}$ (top) and $0.1\text{nm}\leq RMS\leq 5000\text{nm}$ (bottom). The measured thickness fluctuation ($TTV=3.5\mu m$) suffices the predetermined condition $TTV\leq 10\mu m$.

Another 2-inch (50mm ϕ) wafer (B) polished by the same processes has 10 a three-mode distortion with saddle points as shown in Fig.10. A peak height H is $H=2\mu m$. $H=2\mu m$ satisfies the requirement of $H\leq 12\mu m$. AFM-measured roughness is $RMS = 0.2\text{nm}$ to 0.4nm in a sample square of $10\mu m\times 10\mu m$ for both the top and the bottom. The roughness ($RMS = 0.2\text{nm}$ to 0.4nm) also satisfies the requirements $0.1\text{nm}\leq RMS\leq 5\text{nm}$ (top) and 15 $0.1\text{nm}\leq RMS\leq 5000\text{nm}$ (bottom). The fluctuation of thickness was $TTV=3.1\mu m$ at a 0.1mm interval. The thickness fluctuation ($TTV=3.1\mu m$) suffices the condition $TTV\leq 10\mu m$.